

PWP60-WC55ER

Face Material

weight	thickness	material
60 g / m ² ± 10% ISO536	0.07mm ± 10% ISO534	Uncoated white matte paper

Liner

weight	thickness	material
55 g / m ² ± 10% ISO536	0.55mm ± 10% ISO534	Monochrome coated white CCK release paper

Adhesive

ER is a removable weak adhesive acrylic adhesive. It has weak adhesive acrylic adhesive and is not suitable for repeated pasting. Remove the adhesive without residue. It is not suitable for pasting PE bags and oily surface substrates, and is suitable for pasting paper objects in a short time.

Peel adhesion

initial adhesion	20 mins Peel adhesion value on steel at 180 angle	20 mins Peel adhesion value on steel at 90 angle
5 N/25mm or tear off FTM9	3.5 N/25mm or tear off FTM1	3N/25mm or tear off FTM2

Temperature

Min. Appl. Temp. 10 °C	Service Temp. 0°C +90°C (24H after labeling)
------------------------	--

Applications

This is an acrylic adhesive with weak viscosity and is not suitable for repeated pasting. It is not suitable for pasting PE or PVC products, and it is not recommended to apply it to the surface with oil.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Printing Methods

The surface material has excellent ink absorption and is suitable for a variety of printing methods, including laser and inkjet printing. Matte paper with rough surface is suitable for printing and printing simple pictures and texts. It is applied to office, logistics and other industries.

Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.